

# T-Rex Power Fast Grab

Revision: 7/05/2015

Page 1 from 2

**Technical data**

Basis	SMX® Polymer
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 5 min
Curing speed * (20°C / 65% R.H.)	3 mm/24h
Hardness	50 ± 5 Shore A
Density	1,47 g/ml
Elastic recovery (ISO 7389)	> 75 %
Maximum allowed distortion	± 20 %
Temperature resistance	-40 °C → 90 °C
Max. tension (DIN 53504)	3,00 N/mm <sup>2</sup>
Elasticity modulus 100% (DIN 53504)	1,60 N/mm <sup>2</sup>
Elongation at break (DIN 53504)	500 %
Application temperature	5 °C → 35 °C



(\* ) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

**Product description**

T-Rex Power Fast Grab is a high quality, neutral, elastic, 1-component adhesive sealant based on SMX® Polymer with a very high initial tack.

**Properties**

- High initial tack reducing the need for initial support.
- Fast curing
- Good extrudability
- high shear strength after full cure (no primer)
- Stays elastic after curing and very sustainable
- No odour.
- Can be painted with water based systems
- Good colour stability, weather and UV resistance
- Does not contain isocyanates and no silicones
- Good adhesion on wet substrates

**Applications**

- Sealing and bonding in the building and construction industry.
- Elastic bonding of panels, profiles and other pieces on the most common substrates (wood, MDF, chipboard, etc).

- Elastic structural bonding in car and container industry.

**Packaging & Colours:**

290ml cartridge - bright white, steel grey, jet black, quick silver, beach sand.  
600ml sausage - bright white

**Shelf life**

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

**Chemical resistance**

Good resistance to water, aliphatic solvents, hydrocarbons, ketones, esters, alcohols, diluted mineral acids and alkalis and (salt) water. Poor resistance to aromatic solvents, concentrated acids and chlorinated hydrocarbons.

**Liability**

The content of this technical data sheet is the result of tests, monitoring and experience. She is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## T-Rex Power Fast Grab

---

Revision: 7/05/2015

Page 2 from 2

### Substrates

*Substrates:* all usual building substrates, treated wood, PVC, plastics, ...

*Nature:* clean, dry, free of dust and grease.

*Surface preparation:* Porous surfaces in water loaded applications should be primed with Primer 150. All smooth surfaces can be treated with Surface Activator.

T-Rex Power Fast Grab is has been tested on following metal surfaces: AlCuMg1, AlMg3, AlMgSi1, stainless steel, electro-galvanized steel, brass, steel ST1403, hot dip galvanized steel. T-Rex Power also has a good adhesion on plastics: polystyrene, polycarbonate (Makrolon®), PVC, polyamide, fiberglass reinforced epoxy, polyester. While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. For optimum adhesion the use of Surface Activator is recommended. We recommend a preliminary adhesion test on every surface. NOTICE: bonding plastics like PMMA (e.g. Plexi® glass), polycarbonate (e.g. Makrolon® or Lexan®) in stress loaded applications can give rise to stress cracking and crazing in these substrates. The use of T-Rex Power is not recommended in these applications. There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates.

### Joint dimensions

The optimal bond thickness for this product is at least 2 mm for the elastic properties to come to full justice.

### Application method

*Application method:* With manual- or pneumatic caulking gun.

*Cleaning:* Clean with white spirit or Surface Cleaner immediately after use.

*Finishing:* With a soapy solution or Soudal Finishing Solution before skinning.

*Repair:* With the same material

### Health- and Safety Recommendations

Take the usual labour hygiene into account. Consult label for more information.

### Remarks

- T-Rex Power Fast Grab may be overpainted with water based paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- The drying time of alkyd resin based paints may increase.
- T-Rex Power Fast Grab can be applied to a wide variety of substrates. Due to the fact that specific substrates such as plastics, like polycarbonate, etc, may differ from manufacturer to manufacturer, we recommend preliminary compatibility test.
- While producing plastics very often releasing agents, processing aids and other protective agents (like protection foil) are used. These should be removed prior to bonding. For optimum adhesion the use of Surface Activator is recommended.
- T-Rex Power Fast Grab cannot be used as a structural glazing sealant.
- T-Rex Power Fast Grab can be used for bonding of natural stone, but it cannot be used as a joint sealant on this type of surface. T-Rex Power can therefore only be used on the bottom of natural stone tiles.
- When applying, make sure not to spill any sealant on the surface of materials.
- A total absence of UV can cause a colour change of the sealant.

### Environmental clauses

*Leed regulation:*

T-Rex Power conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED® 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions beyond our control, no liability under this publication are accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.