

Characteristics:

- UNIGRIP is a premium grade non rubber, flexible white cement based tile adhesive.
- UNIGRIP is non slip/non slump ideal for large format tiles.
- It is designed for bonding all types of ceramic, stone and mosaic tiles onto a variety of substrates like concrete, render, rendered brickwork, blockwork, Gyprock, plasterboard, fibre cement and appropriately prepared flooring boards.
- It can be used internally or externally on wall and floor surfaces.
- UNIGRIP can be used for fixing Porcelain and Vitrified tiles.
- UNIGRIP can be used to fix tiles over existing tiles as long as the existing tiles have been coated with RLA Universal Primer.
- UNIGRIP can be used over particle board flooring see instructions in preparation.
- UNIGRIP can be used to fix tiles over most waterproofing membranes. However it is advisable to contact the manufacturer prior to commencing.
- UNIGRIP can be used for fixing tiles in fully immersed situations like swimming pools and spas.
- Contact your RLA office for more information 1800 752 679.
- UNIGRIP can be used over some acoustic mats please contact RLA for more information.
- Do not use UNIGRIP for moisture sensitive stone like green marble.

Preparation:

- UNIGRIP is suitable for use over 7 day old concrete which has a woodfloat finish.
- All rendered surfaces must be allowed to cure for at least 24 hours prior to commencing tiling.
- The maximum variation in the plane of the concrete must not exceed 5mm in 3 meters for floors and 4mm in 2 meters for walls.
- Steel trowelled finished concrete surfaces must be mechanically or abraded prior to commencing tiling.
- Structural Particle Board used as a flooring material must be a minimum of 19mm thick, fixed in accordance with the manufacturer's instructions and the relevant standards must be heavily sanded with a 30 grit sander to remove the dark surface of the flooring board. Once completed apply RLA Universal primer neat and wait 2 hours @20°C before tiling commences. (Because the quality and nature of coatings used on Structural flooring boards is sometimes unknown please contact the Technical centre for more information on 1800 752 679.
- Fibre Cement sheet when used as an underlay must be a minimum of 5mm in thickness. For heavy duty commercial applications it should be a minimum of 9mm thick and all should be fixed in accordance with the manufacturers instructions and the relevant standards.
- Compressed Fibre-Cement sheets when used as a floor substrate must be 15mm thick and when used as a wall substrate must be 9mm thick and must be installed in accordance with the manufacturer's instructions and therelevant standards.
- Gypsum - plasterboard sheets when used as a wall substrate must be a minimum of 10mm thick and installed in accordance with the manufacturer's instructions and the relevant standards.
- The movement joints must be installed as per AS3958:2007.
- Ensure all surfaces are sound, dry and free from excessive movement, oil, dust, grease, wax, curing compounds, release agents and any other loose contaminating materials.

- Premium grade Polymer modified non-rubber flexible white cement based tile adhesive
- Fibre reinforced
- Non slump
- Ideal for large format tiles
- Internal / external wall / floor
- Complies with AS ISO 13007.1-2013 Class C2S2T



- All porous surfaces like concrete, screeds, fibre cement sheet etc. should be primed using RLA Universal primer.
- When applying the primer onto a floor surface it is recommended to firstly pour some primer in a section then spread the primer using a broom, brush or roller. Then continue this method of application until the entire area is primed. Note: This method of application ensures a thorough coat of the primer on the surface.
- Allow the primer to dry for approximately 30-40 minutes at 20°C prior to commencing tiling.
- Any excess Universal primer that has not dried should be removed with a rag prior to tiling.

Expansion | Movement Joints:

Expansion / movement joints must be provided to allow for movement between adjacent building components.

They should be as follows:

Over Existing joints in the substrate.

- Where two different substrates meet. e.g. Timber and Concrete.
- Around fixed elements in the floor e.g. Columns.
- At internal vertical corners.
- Around the perimeter of the floor. ·In internal floors where any dimension exceeds 9m or 6m if subjected to sunlight. Framed floors should have an expansion joint every 4.5m In external floors where any dimension exceeds 4.5 m.
- On wall surfaces at storey heights horizontally and approximately 3m-4.5m apart vertically. Ideally they should be located over movement joints in the structural background and at structural material changes, for example the horizontal joint at the bottom of floor slabs, vertical joints at internal vertical corners, and at junctions with columns.
- Movement joints should go right through the tile adhesive bed to the background and be kept free from dirt and adhesive droppings. Movement joints must not be less than 6mm and not wider than 10mm.
- The movement joints must be installed as per AS3958:2007.

Mixing:

- The mixing ratio of UNIGRIP is 4.5 litres of water to each 15kg bag. Pour water into a clean drum. Gradually add the UNIGRIP powder while mixing continuously until a smooth lump free mix is obtained.
- Always add powder to liquid.
- Allow to stand for 10 minutes, re stir then apply the adhesive onto the substrate.

Application:

- All tiling should be carried out in accordance with Australian Standard AS3958.1-2007.
- Once the surface has been appropriately prepared in accordance with RLA instructions then apply the adhesive onto the substrate using an appropriate notched trowel.
For floor tiling use a 10mm x 10mm square notched trowel for tiles up to 300mm x 300mm. For tiles 300mm x 300mm and larger use a 12mm x 12mm square notched trowel and back butter each tile. For mosaic tiles use a 6mm x 6mm square notched trowel.
- For wall tiling use Bmm x Bmm square notched trowel for tiles up to 150mm x 150mm. For tiles larger than 150mm x 150mm use a 10mm x 10mm square notched trowel.
- UNIGRIP should be applied onto the substrate at a rate of 1 m² at a time. Application rates greater than this can result in the tile adhesive skinning before the tiles are laid into it.
- Once the adhesive is applied onto the substrate ensure that it does not skin prior to bedding the tiles into it. Once the adhesive skins do not lay tiles into it, but remove it and apply fresh adhesive.
- When placing the tiles into the adhesive press them in by using a sliding action. Ensure no voids occur and full coverage of adhesive is under the tiles.
- For tiles with lugs, grooves or uneven backing it may be required to butter the back of the tile with adhesive in addition to trowelling the adhesive onto the substrate.
- The final bed thickness of the adhesive should be at least 2mm for wall tiling and 3mm for floor tiling.
- Once the tiling is completed do not disturb the tiled surface for at least 24 hours at 20°C.
- Protect tiling from rain and inclement weather until 24 hours after grouting is complete.

Clean up:

- Excess adhesive from tile face of the tiles can be cleaned up with damp cloth while the adhesive is still wet.
- Adhesive that has oozed out into the grout joint must be raked out with a knife/spatula etc.
- Tools and other equipment can be cleaned up using water while the adhesive is still wet.

Coverage:

- A 15kg bag of UNIGRIP will cover approximately 6-7m using a 10mm notched trowel.

Grouting Application:

- Grouting application can commence 24 hours after the completion of tiling.
- After grouting allow to cure undisturbed for 24 hours at 20°C before putting area into service.

Packaging | Shelf Life:

- UNIGRIP is available in 15kg bags.
- A bag of UNIGRIP, when stored in a cool, dry environment, and is stored above ground level, will have a shelf life of approximately 12 months.

Handy Tips:

- Do not apply UNIGRIP in temperatures above 40°C and below 5°C.
- UNIGRIP cannot be used for fixing tiles directly onto tongue and groove timber flooring.
- For applications / situations not mentioned in these instructions please contact your nearest RLA office.
- UNIGRIP being cement based is alkaline in nature, and therefore may cause dermatitis. It is recommended that applicators wear PVC gloves or similar and safety goggles.
- For a full MSDS on this product please contact your nearest RLA office.

Safety Directions:

- Hazardous - Contains cement silica. Wear gloves and mask when handling. Wash hands thoroughly after use.

Manual Handling:

- Manual handling of this bag without due care and attention may result in personal injury.

Disclaimer: The information supplied is to the best of our knowledge true and accurate. The actual application of the product is beyond the manufacturers control. Any failure or damage caused by the incorrect usage of the product is not the responsibility of the manufacturer. The manufacturer insists that all workmanship must be carried out in accordance with AS 3958.1-2007. It is also the responsibility of the end user to ensure that the literature in their possession is the latest issue.

Technical Data

Appearance	White Powder	Pot Life	2 hours @ 20°C
Bulk Density	1.18 +/- 0.05	Ready for grouting	24 hours @ 20°C
Open Time	Approx 30 minutes @ 20°C	Light foot traffic	24 hours
Adjustment Time	Approx 30 minutes @ 20°C	Ready for wet area service	3-4 days



RLA Polymers Pty Ltd
ACN 004 709 915
215 Colchester Road,
Kilsyth, Victoria 3137
Australia

Tel: 1800 242 931
Fax: 1800 627 943
sales@rlagroup.com.au
www.rlagroup.com.au